



Ballistic Testing of SSAB Ultra-High-Hardness Steel for Armor Applications

**by Dwight D. Showalter, William A. Gooch, Matthew S. Burkins,
and R. Stockman Koch**

ARL-TR-4632

October 2008

NOTICES

Disclaimers

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer needed. Do not return it to the originator.

Army Research Laboratory

Aberdeen Proving Ground, MD 21005-5069

ARL-TR-4632**October 2008**

Ballistic Testing of SSAB Ultra-High-Hardness Steel for Armor Applications

Dwight D. Showalter, William A. Gooch, and Matthew S. Burkins
Weapons and Materials Research Directorate, ARL

R. Stockman Koch
SSAB Oxelosund AB

REPORT DOCUMENTATION PAGE				Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing the burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.					
1. REPORT DATE (DD-MM-YYYY) October 2008		2. REPORT TYPE Final		3. DATES COVERED (From - To) April 2008–August 2008	
4. TITLE AND SUBTITLE Ballistic Testing of SSAB Ultra-High-Hardness Steel for Armor Applications				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S) Dwight D. Showalter, William A. Gooch, Matthew S. Burkins, and R. Stockman Koch*				5d. PROJECT NUMBER 1L16226188H80	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army Research Laboratory ATTN: AMSRD-ARL-WM-TA Aberdeen Proving Ground, MD 21005-5069				8. PERFORMING ORGANIZATION REPORT NUMBER ARL-TR-4632	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.					
13. SUPPLEMENTARY NOTES *SSAB Oxelosund AB, SE-613 80 Oxelosund, Sweden					
14. ABSTRACT The highest-performing U.S. steel alloys for armor-piercing (AP) bullet protection are manufactured to MIL-DTL-46100E, high-hardness armor (HHA) with a hardness range of 477–534 Brinell hardness number (BHN), and to MIL-A-46099C, dual hardness armor (DHA), which is produced by roll bonding a 601–712 BHN front plate to a 461–534 BHN back plate. While these materials still serve their intended applications, monolithic ultra-high-hardness (UHH) steels with a hardness of 600 BHN or greater have been developed. This class of steels increases AP bullet defeat, reduces armor weight, and eliminates the manufacturing difficulties inherent in DHA. Swedish Steel Oxelösund AB (SSAB) produces a number of grades of steel, which have previously been assessed against AP ammunition. However, SSAB has two UHH armor steels designated ARMOX 600T and ARMOX ADVANCE that meet this hardness criteria. ARMOX 600T is a nominal 600 BHN steel while ARMOX ADVANCE has a nominal hardness of Rockwell C58-63 (>650 BHN). This report assesses the performance of these steels against two projectiles that will be used to generate a new military specification for UHH steel armor. The performance of these UHH steels will be compared to the current HHA MIL-DTL-46100E specification.					
15. SUBJECT TERMS armor plate, steel, armor piercing, ultra-high hard					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT	18. NUMBER OF PAGES	19a. NAME OF RESPONSIBLE PERSON
a. REPORT UNCLASSIFIED	b. ABSTRACT UNCLASSIFIED	c. THIS PAGE UNCLASSIFIED			Dwight D. Showalter
			UL	52	19b. TELEPHONE NUMBER (Include area code) 410-278-7308

Contents

List of Figures	iv
List of Tables	v
1. Introduction	1
2. ARMOX Steels	2
3. Experimental Procedure	2
4. Test Projectiles	4
5. Results and Discussion	4
6. Conclusions	8
7. References	9
Appendix A. ARMOX ADVANCE Photographs	11
Appendix B. ARMOX 600T Photographs	15
Appendix C. Data Sheets	19
Distribution List	37

List of Figures

Figure 1. Production flow diagram at SSAB for ARMOX steel plate manufacture.....	3
Figure 2. The 0.30-cal. APM2 and 0.50-cal. APM2 test projectiles.....	5
Figure 3. ARMOX 600T and ARMOX ADVANCE plate thickness vs. V_{50} velocity for the 0.30-cal. APM2 at 30° obliquity.....	6
Figure 4. ARMOX 600T and ARMOX ADVANCE plate thickness vs. V_{50} velocity for the 0.50-cal. APM2 at 30° obliquity.....	7
Figure A-1. ARMOX ADVANCE (0.30 cal.): 4.8 mm (a) front and (b) back.....	12
Figure A-2. ARMOX ADVANCE (0.30 cal.): 5 mm (a) front and (b) back.....	12
Figure A-3. ARMOX ADVANCE (0.30 cal.): 6 mm (a) front and (b) back.....	12
Figure A-4. ARMOX ADVANCE (0.30 cal.): 7 mm (a) front and (b) back.....	13
Figure A-5. ARMOX ADVANCE (0.30 cal.): 8 mm (a) front and (b) back.....	13
Figure A-6. ARMOX ADVANCE (0.50 cal.): 8 mm (a) front and (b) back.....	13
Figure A-7. ARMOX ADVANCE (0.50 cal.): 10 mm (a) front and (b) back.....	14
Figure A-8. ARMOX ADVANCE (0.50 cal.): 12 mm (a) front and (b) back.....	14
Figure B-1. ARMOX 600T (0.30 cal.): 4.8 mm (a) front and (b) back.....	16
Figure B-2. ARMOX 600T (0.30 cal.): 5 mm (a) front and (b) back.....	16
Figure B-3. ARMOX 600T (0.30 cal.): 6 mm (a) front and (b) back.....	16
Figure B-4. ARMOX 600T (0.30 cal.): 7 mm (a) front and (b) back.....	17
Figure B-5. ARMOX 600T (0.30 cal.): 8 mm (a) front and (b) back.....	17
Figure B-6. ARMOX 600T (0.50 cal.): 8 mm (a) front and (b) back.....	17
Figure B-7. ARMOX 600T (0.50 cal.): 10 mm (a) front and (b) back.....	18
Figure B-8. ARMOX 600T (0.50 cal.): 12 mm (a) front and (b) back.....	18

List of Tables

Table 1. Chemical composition of ARMOX plate.	3
Table 2. Mechanical properties of ARMOX plate.....	3
Table 3. Projectile and obliquity requirements for ordered thicknesses.....	4
Table 4. ARMOX 600T and ARMOX ADVANCE plate vs. the 0.30-cal. APM2 projectile at 30° obliquity.	5
Table 5. ARMOX 600T and ARMOX ADVANCE plate vs. 0.50-cal. APM2 at 30° obliquity.	6

INTENTIONALLY LEFT BLANK.

1. Introduction

The U.S. armor community is currently engaged in accelerated efforts to deliver lightweight armor technologies that can defeat armor-piercing (AP) projectiles at reduced areal weights that are available across a large industrial base. While many of these programs involve the application of lower-density metals such as aluminum and titanium, the selection of steel alloys is still competitive for many ballistic and structural applications; the ability to fabricate armor components in both commercial and military operational areas with available equipment and personnel is a major advantage of steel solutions. To meet these requirements, the U.S. armor community has increased the availability of quenched and tempered armor steels by updating current steel military specifications—the most important has been the updated MIL-DTL-46100E specification for high-hardness armor (HHA) (1). This improved specification was necessary to supply the large steel demands for combat operations in Iraq and Afghanistan. This HHA specification allows modern continuous processing technologies to be used efficiently and offers a new class of auto-tempered high-hard steels.

Currently, the highest-performing U.S. steel alloys for AP bullet protection are manufactured to MIL-DTL-46100E, HHA with a hardness range of 477–534 Brinell hardness number (BHN), and to MIL-A-46099C, dual hardness armor (DHA), which is produced by roll bonding a 601–712 BHN front plate to a 461–534 BHN back plate (2). The roll-bonded DHA steels are complex to produce and have known production limitations. The U.S. Army Research Laboratory (ARL), in conjunction with the Institute of Metal Science of Sofia, Bulgaria, examined improved steel technologies to produce these DHA steels by electroslag remelting processes, but producing DHA steels remains difficult (3). While both these metal specifications serve their intended applications, considerable overseas efforts to develop monolithic ultra-high-hardness (UHH) steels with a hardness of 600 BHN or greater have been accomplished, and significant advancements in steel metallurgy have been noted in Sweden, Germany, and France. The improved ballistic resistance of steel as a function of increasing hardness is well established in the ballistic community, particularly by Rapacki et al. in the 15th Ballistics Symposium (4). This class of steels should increase AP bullet defeat, reduce armor weight, and eliminate the manufacturing difficulties inherent in DHA. This report will document the development of a new class of ballistic UHH steels that will be defined in a new military specification. There are additional UHH steels known or in development that could meet this specification.

Swedish Steel Oxelösund AB (SSAB) produces a number of grades of steel that have previously been assessed against AP projectiles by ARL (5). However, SSAB currently has available two UHH armor steels designated ARMOX 600T (6) and ARMOX ADVANCE (7) that will form the basis of this new specification. Limited evaluation of ARMOX 600T was conducted in Rapacki et al. (4), but this work expands upon that data. ARMOX 600T has a hardness of 570–640 BHN

while ARMOX ADVANCE has a nominal hardness of Rockwell C58–63 (>650 BHN). This study assesses the performance of these steels against two projectiles that will be used to generate a new military specification for ultra hard steel with two hardness classes: class 1 (513–640 BHN) and class 2 (over 640 BHN). The performance of the ARMOX steels will be compared to the current ballistic acceptance requirements of MIL-DTL-46100E.

2. ARMOX Steels

SSAB develops, manufactures, and markets heavy steel plate and is located south of Stockholm, Sweden, on the Baltic coast. SSAB ballistic plate is manufactured under the designation ARMOX and is available in hardness ranges from rolled homogeneous armor steel (280 BHN) to UHH steel (>640 BHN). ARMOX steels are known for high toughness in relation to the hardness. ARMOX 600T has been available on the market for about 10 years and is mostly used as appliqué armor in various applications in combination with steel, aluminum, composites, or other materials. ARMOX ADVANCE is the newest member of the ARMOX family and is also intended for appliqué armor. As weight is a critical factor in many vehicle projects, the aim is to offer a higher mass efficiency.

ARMOX steels are produced from iron-ore-based metallurgy through blast furnaces, steel deoxidation in an LD converter, and vacuum treatment, thus resulting in very clean steel. The modern four-high plate mill allows the possibility to roll with large reductions, resulting in a fine-grained microstructure. Depending on the hardness/toughness requirements, the steel undergoes various heat treatments to achieve final properties. The continuous casting production flow and heat treatment line at SSAB are shown in figure 1. The chemical composition and mechanical properties of three ARMOX alloys are shown in tables 1 and 2. ARMOX 500T has a hardness and ballistic performance that meet the current MIL-DTL-46100E specification and is representative of current high-hardness steels.

3. Experimental Procedure

The ballistic performance of ARMOX 600T and ARMOX ADVANCE steel plates was determined by obtaining the V_{50} ballistic limit for each plate thickness against the corresponding specified test projectile. The test methodology is described in detail in the MIL-STD-662F (8). The V_{50} ballistic limit is the velocity at which an equal number of fair impact complete penetration (target is defeated) and partial penetration (target is not defeated) velocities are attained using the up-and-down firing method. Fair impact is defined as occurring when a projectile with an acceptable yaw strikes the target at a distance of at least two projectile




Figure 1. Production flow diagram at SSAB for ARMOX steel plate manufacture.

Table 1. Chemical composition of ARMOX plate.

Grade	C max (%)	Si (%)	Mn max (%)	P max (%)	S max (%)	Cr max (%)	Ni max (%)	Mo max (%)	B max (%)
ARMOX 500T	0.32	0.1–0.4	1.2	0.015	0.010	1.0	1.8	0.7	0.005
ARMOX 600T	0.47	0.1–0.7	1.0	0.010	0.005	1.5	3.0	0.7	0.005
ARMOX ADVANCE	0.47	0.1–0.7	1.0	0.010	0.005	1.5	3.0	0.7	0.005

Table 2. Mechanical properties of ARMOX plate.

Grade	Hardness (BHN)	Charpy-V –40 °C 10 × 10 mm (J)	0.2%Yield Strength (N/mm ²)	Tensile Strength (N/mm ²)	Elongation (%)
ARMOX 500T	480–540	Minimum 25	Minimum 1250	1450–1750	Minimum 8
ARMOX 600T	570–640	Minimum 12	1500 ^a	2000 ^a	7 ^a
ARMOX ADVANCE	RC58-63	14 ^a	1600 ^a	2250 ^a	9 ^a

^aTypical values.

diameters from a previously damaged impact area or edge of plate. A complete penetration is determined by placing a 0.5-mm (0.020-in) 2024T3 aluminum witness plate 152.6 mm (6.00 in) behind and parallel to the target. If any penetrator or target fragment strikes this witness plate with sufficient energy to create a hole through which light passes, the result is considered a complete penetration. A partial penetration is any impact that is not a complete penetration. For the MIL-DTL-46100E (MR) specification, the V_{50} ballistic limit is defined as the average of six fair impact velocities comprising the three lowest velocities resulting in complete penetration and the three highest velocities resulting in partial penetration. A maximum spread of 45.7 m/s (150 fps) shall be permitted between the lowest and highest velocities employed in determining ballistic limits. The data for the two ARMOX steels are compared to the baseline data of MIL-DTL-46100E.

4. Test Projectiles

The ARMOX plate samples for this report ranged in thickness (nominal) from 0.189 in (4.8 mm) up to 0.472 in (12 mm). The corresponding test projectiles and plate obliquities required for each thickness under MIL-DTL-46100E are listed in table 3. The 0.30-cal. APM2 steel core weighs 5.2 g; with the copper jacket and lead filler, the total projectile weight is 10.6 g. The total length of the projectile is 35.6 mm (1.4 in). This projectile is shown in figure 2. The 0.50-cal. APM2 also has a steel core along with a copper jacket and lead filler. The steel core weighs 25.4 g with a total weight of 44.9 g. The total length is 57.5 mm (2.26 in). Figure 2 also shows this projectile in detail.

5. Results and Discussion

The V_{50} ballistic limits and standard deviation, σ , for each plate thickness against the 0.30-cal. APM2 were determined experimentally for both the ARMOX 600T and ARMOX ADVANCE plates; the data is shown in table 4. Figure 3 plots the V_{50} velocities vs. the plate thickness for the ARMOX 600T and ARMOX ADVANCE plates, as well as the velocity specification

Table 3. Projectile and obliquity requirements for ordered thicknesses.

Ordered Thickness Nominal mm (in)	Projectile ^a	Angle of Obliquity (°)
4.8 (0.189)–8.00 (0.315)	0.30-cal. AP	30
8.00(0.315)–12.0 (0.472)	0.50-cal. AP	30

^aTwo types of projectiles are required for the nominal thickness 8 mm (0.315 in).




Figure 2. The 0.30-cal. APM2 and 0.50-cal. APM2 test projectiles.

Table 4. ARMOX 600T and ARMOX ADVANCE plate vs. the 0.30-cal. APM2 projectile at 30° obliquity.

Steel	Nominal Thickness (mm)	Actual Thickness mm (in)	Obliquity Angle (°)	V ₅₀ m/s (ft/s)	Standard Deviation m/s (ft/s)
600T	4.8	4.52 (0.178)	30	723.0 (2372)	13.4 (44)
600T	5	5.46 (0.215)	30	760.1 (2494)	15.2 (50)
600T	6	6.32 (0.249)	30	781.8 (2565)	10.1 (33)
600T	7	7.42 (0.292)	30	863.2 (2832)	15.2 (50)
600T	8	8.36 (0.329)	30	891.5 (2925)	14.3 (47)
Advance	4.8	4.52 (0.178)	30	666.6 (2187)	14.0 (46)
Advance	5	5.38 (0.212)	30	819.0 (2687)	17.4 (57)
Advance	6	6.40 (0.252)	30	859.5 (2820)	13.4 (44)
Advance	7	7.34 (0.289)	30	905.5 (2971)	17.1 (56)
Advance	8	8.33 (0.328)	30	892.4 (2928)	12.2 (40)




Figure 3. ARMOX 600T and ARMOX ADVANCE plate thickness vs. V₅₀ velocity for the 0.30-cal. APM2 at 30° obliquity.

requirements for high-hard steel (MIL-DTL-46100E). The 2σ curve (V₅₀ – 2σ) is also plotted for each steel; this curve accounts for the fact that the V₅₀ only provides the velocity at which the armor defeats the penetrator 50% of the time. Subtracting 2σ from the V₅₀ velocity provides the statistical velocity at which the armor will defeat the penetrator 98% of the time. The V₅₀ ballistic limits and σ for each plate thickness against the 0.50-cal. APM2 for ARMOX 600T and ARMOX ADVANCE plates are shown in table 5. Figure 4 plots the V₅₀ vs. the plate thickness for the ARMOX 600T and ARMOX ADVANCE plates, as well as the specification requirements for high-hard steel (MIL-DTL-46100E).

Table 5. ARMOX 600T and ARMOX ADVANCE plate vs. 0.50-cal. APM2 at 30° obliquity.

Steel	Nominal Thickness (mm)	Actual Thickness mm (in)	Obliquity Angle (°)	V ₅₀ m/s (ft/s)	Standard Deviation m/s (ft/s)
600T	8	8.36 (0.329)	30	691.9 (2270)	6.5 (28)
600T	10	10.41 (0.410)	30	754.3 (2475)	13.1 (43)
600T	12	12.25 (0.482)	30	826.0 (2710)	14.3 (47)
Advance	8	8.33 (0.328)	30	725.7 (2381)	11.0 (36)
Advance	10	10.29 (0.405)	30	788.2 (2586)	14.3 (47)
Advance	12	12.24 (0.482)	30	824.7 (2706)	13.4 (44)




Figure 4. ARMOX 600T and ARMOX ADVANCE plate thickness vs. V_{50} velocity for the 0.50-cal. APM2 at 30° obliquity.

The ballistic advantage of increased hardness can be seen in figures 3 and 4 where both the ARMOX 600T and ARMOX ADVANCE are significantly better-performing steels than standard high-hard steels. The data points for each thickness are plotted, and a second order fit to the data is shown in the solid lines. The solid lines at the bottom of the graphs are also second order fits that define the acceptance velocities under MIL-DTL-46100E for the respective thickness. These lines already incorporate $\sim 2\sigma$ reduction, which provides an acceptable variance to allow the high-hard plate to meet the specification. Therefore, the best direct comparisons to the baseline high-hard acceptance lines are the dashed 2σ lines of the ARMOX 600T and ARMOX ADVANCE plates over the thickness range tested.

The 0.30-cal. data for both ARMOX steels of figure 3 show a performance inflection in the data at the 4.8-mm thickness and equivalent performance at 8-mm thicknesses. The 4.8-mm data point probably results from projectile diameter/thickness effects on the plugging mechanism, and the equivalent performance at 8 mm probably results from a minimum hardness needed to stop the projectile when the projectile diameter and plate thickness are similar. The ARMOX ADVANCE is statistically better than the ARMOX 600T in the thickness range of 5, 6, and 7 mm. The ARMOX ADVANCE exhibited some cracking during testing, but the test plates were only 305 mm (12 in) wide, and cracking originated from the cut edges.

The 0.50-cal. data of figure 4 consisted of only three thicknesses and showed the same equivalence at the 12-mm thickness where the projectile diameter approaches the plate thickness.

Both showed significant increased performance over the baseline MIL-DTL-46100 high-hard steel. Some cracking was also noted from the 305-mm (12-in)-wide test plates; this can be eliminated by proper edge treatment after cutting.

6. Conclusions

This report has documented the increased performance that results from increased plate hardness. Both the ARMOX 600T and ARMOX ADVANCE plates showed significant ballistic performance increases in the thickness range tested over standard MIL-DTL-46100E high-hardness plate. This data will form part of the ballistic data that will be used to create a new US steel specification for UHH steel plate. The specification will include two classes of hardness that will cover the hardness range from 513 to over 650 BHN. This new class of ultra-hard steel plates will increase the metallic armor technologies available to armor designers.

7. References

1. MIL-DTL-46100E (MR). *Armor Plate, Steel, Wrought, High-Hardness* **2008**.
2. MIL-A-46099C. *Armor Plate, Steel, Roll-Bonded, Dual Hardness (0.187 Inches to 0.700 Inches Inclusive)* **1987**.
3. Gooch, W.; Burkins, M.; MacKenzie, D.; Vodenicharov, S. Ballistic Analysis of Bulgarian Electroslag Remelted High Hard Steel Armor Plate. *Proceedings of the 22nd International Symposium on Ballistics*, Vancouver, British Columbia, Canada, 14–18 November 2005.
4. Rapacki, E.; Frank, K.; Leavy, B.; Keele, M.; Prifti, J. Armor Steel Hardness Influence on Kinetic Energy Penetration. *Proceedings of the 15th International Symposium on Ballistics*, Jerusalem, Israel, May 1995.
5. Gooch, W. A.; Burkins, M. S.; Squillacioti, R.; Stockman Koch, R.; Oscarsson, H.; Nash, C. Ballistic Testing of Swedish Steel for U.S. Armor Applications. *The 21st International Symposium on Ballistics*, Adelaide, Australia, 19–23 April 2004.
6. SSAB Data Sheet, ARMOX 600T, Version 2007-10-1. Swedish Steel Oxelösund AB, Sweden, 2007.
7. SSAB Data Sheet, ARMOX ADVANCE, Version 2007-10-1. Swedish Steel Oxelösund AB, Sweden, 2007.
8. MIL-STD-662F. *V50 Ballistic Test for Armor* **1997**.

INTENTIONALLY LEFT BLANK.

Appendix A. ARMOX ADVANCE Photographs



Figure A-1. ARMOX ADVANCE (0.30 cal.): 4.8 mm (a) front and (b) back.



Figure A-2. ARMOX ADVANCE (0.30 cal.): 5 mm (a) front and (b) back.



Figure A-3. ARMOX ADVANCE (0.30 cal.): 6 mm (a) front and (b) back.




Figure A-4. ARMOX ADVANCE (0.30 cal.): 7 mm (a) front and (b) back.



Figure A-5. ARMOX ADVANCE (0.30 cal.): 8 mm (a) front and (b) back.



Figure A-6. ARMOX ADVANCE (0.50 cal.): 8 mm (a) front and (b) back.




Figure A-7. ARMOX ADVANCE (0.50 cal.): 10 mm (a) front and (b) back.



Figure A-8. ARMOX ADVANCE (0.50 cal.): 12 mm (a) front and (b) back.

Appendix B. ARMOX 600T Photographs



Figure B-1. ARMOX 600T (0.30 cal.): 4.8 mm (a) front and (b) back.




Figure B-2. ARMOX 600T (0.30 cal.): 5 mm (a) front and (b) back.



Figure B-3. ARMOX 600T (0.30 cal.): 6 mm (a) front and (b) back.




Figure B-4. ARMOX 600T (0.30 cal.): 7 mm (a) front and (b) back.




Figure B-5. ARMOX 600T (0.30 cal.): 8 mm (a) front and (b) back.



Figure B-6. ARMOX 600T (0.50 cal.): 8 mm (a) front and (b) back.




Figure B-7. ARMOX 600T (0.50 cal.): 10 mm (a) front and (b) back.



Figure B-8. ARMOX 600T (0.50 cal.): 12 mm (a) front and (b) back.

Appendix C. Data Sheets

This appendix appears in its original form, without editorial change.

Plate Type:	Armox Advance
Nominal Thickness (mm)	4.8
Nominal Thickness (in)	0.189
Measured Thick. (in)	0.178
BHN	600
Penetrator:	.30 AP M2
Obliquity:	30
Date:	14-May-08

Shot #	Velocity (ft/s)	Velocity (m/s)	Result
6490	1916	584	PP
6491	2033	620	PP +
6492	2128	649	CP
6493	2091	638	PP -
6494	2161	659	PP
6495	2139	652	PP -
6496	2169	661	PP +
6497	2249	686	CP -
6498	2180	665	PP
6499	2232	680	PP

Low CP	2128
High PP	2180

	(ft/s)	m/s
V50	2187	667
Std Dev	46	14
Vel Spread	121	37
ZMR	52	16

Plate Type:	Armox Advance
Nominal Thickness (mm)	5
Nominal Thickness (in)	0.197
Measured Thick. (in)	0.212
BHN	600
Penetrator:	.30 AP M2
Obliquity:	30
Date:	15-May-08

Shot #	Velocity (ft/s)	Velocity (m/s)	Result
6506	2222	677	PP
6507	2366	721	PP
6508	2470	753	PP
6509	2592	790	PP-
6510	2726	831	CP+
6511	2679	817	PP-
6512	2726	831	CP+
6513	2741	836	CP+
6514	2655	809	PP-

Low CP	2726
High PP	2679

	(ft/s)	m/s
V50	2687	819
Std Dev	57	17
Vel Spread	149	45
ZMR	0	0

Plate Type:	Armox Advance
Nominal Thickness (mm)	6
Nominal Thickness (in)	0.236
Measured Thick. (in)	0.252
BHN	600
Penetrator:	.30 AP M2
Obliquity:	30
Date:	16-May-08

Shot #	Velocity (ft/s)	Velocity (m/s)	Result
6523	2778	847	PP -
6524	2880	878	CP +
6525	2843	867	CP +
6526	2820	860	CP +
6527	2780	848	PP -
6528	2769	844	PP -

Low CP	2820
High PP	2780

	(ft/s)	m/s
V50	2812	857
Std Dev	44	13
Vel Spread	111	34
ZMR	0	0

Plate Type:	Armox Advance
Nominal Thickness (mm)	7
Nominal Thickness (in)	0.276
Measured Thick. (in)	0.289
BHN	600
Penetrator:	.30 AP M2
Obliquity:	30
Date:	19-May-08

Shot #	Velocity (ft/s)	Velocity (m/s)	Result
6529	2893	882	PP -
6530	2920	890	PP -
6532	2971	906	PP -
6532	3040	927	CP +
6533	3013	919	CP +
6534	2990	912	CP +

Low CP	2990
High PP	2971

	(ft/s)	m/s
V50	2971	906
Std Dev	56	17
Vel Spread	147	45
ZMR	0	0

Plate Type:	Armox Advance
Nominal Thickness (mm)	8
Nominal Thickness (in)	0.315
Measured Thick. (in)	0.328
BHN	600
Penetrator:	.30 AP M2
Obliquity:	30
Date:	15-May-08

Shot #	Velocity (ft/s)	Velocity (m/s)	Result
6500	2990	912	CP +
6501	2871	875	PP -
6502	2926	892	CP +
6503	2910	887	PP -
6504	2918	890	PP -
6505	2953	900	CP +

Low CP	2926
High PP	2918

	(ft/s)	m/s
V50	2928	893
Std Dev	40	12
Vel Spread	119	36
ZMR	0	0

Plate Type:	Armox Advance
Nominal Thickness (mm)	8
Nominal Thickness (in)	0.315
Measured Thick. (in)	0.328
BHN	578
Penetrator:	.50 AP M2
Obliquity:	30
Date:	6-May-08

Shot #	Velocity (ft/s)	Velocity (m/s)	Result
6456	2188	667	PP
6457	2369	722	PP -
6458	2509	765	CP
6459	2409	734	CP +
6460	2389	728	PP -
6461	2415	736	CP +
6462	2391	729	CP +
6463	2315	706	PP -

Low CP	2391
High PP	2389

	(ft/s)	m/s
V50	2381	726
Std Dev	36	11
Vel Spread	100	30
ZMR	0	0

Plate Type:	Armox Advance
Nominal Thickness (mm)	10
Nominal Thickness (in)	0.394
Measured Thick. (in)	0.405
BHN	600
Penetrator:	.50 AP M2
Obliquity:	30
Date:	12-May-08

Shot #	Velocity (ft/s)	Velocity (m/s)	Result
6473	2507	764	PP
6474	2582	787	PP -
6475	2741	836	CP
6476	2709	826	CP
6477	2665	813	CP
6478	2662	812	CP +
6479	2596	791	CP +
6480	2552	778	PP -
6481	2598	792	CP +
6482	2523	769	PP -

Low CP	2596
High PP	2582

	(ft/s)	m/s
V50	2586	788
Std Dev	47	14
Vel Spread	139	42
ZMR	0	0

	Armox
Plate Type:	Advance
Nominal Thickness (mm)	12
Nominal Thickness (in)	0.472
Measured Thick. (in)	0.482
BHN	600
Penetrator:	.50 AP M2
Obliquity:	30
Date:	2-May-08

Shot #	Velocity (ft/s)	Velocity (m/s)	Result
6448	2497	761	PP
6449	2640	805	PP -
6450	2840	866	CP
6451	2729	832	CP +
6452	2697	822	PP -
6453	2730	832	CP +
6454	2677	816	PP -
6455	2762	842	CP +

Low CP	2596
High PP	2582

	(ft/s)	m/s
V50	2586	788
Std Dev	47	14
Vel Spread	139	42
ZMR	0	0

Plate Type:	Armox 600T
Nominal Thickness (mm)	6
Nominal Thickness (in)	0.236
Measured Thick. (in)	0.249
BHN	627
Penetrator:	.30 AP M2
Obliquity:	30
Date:	1-Jul-08

Shot #	Velocity (ft/s)	Velocity (m/s)	Result
7246	2712	827	CP
7247	2620	799	CP
7248	2440	744	PP
7249	2540	774	PP -
7250	2586	788	PP -
7251	2603	794	CP +
7252	2594	791	CP +
7253	2540	774	CP +
7254	2527	770	PP -

Low CP	2540
High PP	2586

	(ft/s)	m/s
V50	2565	782
Std Dev	33	10
Vel Spread	76	23
ZMR	46	14

Plate Type:	Armox 600T
Nominal Thickness (mm)	4.8
Nominal Thickness (in)	0.189
Measured Thick. (in)	0.178
BHN	627
Penetrator:	.30 AP M2
Obliquity:	30
Date:	6-Jul-08

Shot #	Velocity (ft/s)	Velocity (m/s)	Result
7261	2333	711	PP -
7262	2437	743	CP +
7263	2384	727	CP +
7264	2320	707	PP -
7265	2355	718	PP -
7266	2402	732	CP +

Low CP	2384
High PP	2355

	(ft/s)	m/s
V50	2372	723
Std Dev	44	13
Vel Spread	117	36
ZMR	0	0

Plate Type:	Armox 600T
Nominal Thickness (mm)	5
Nominal Thickness (in)	0.197
Measured Thick. (in)	0.215
BHN	627
Penetrator:	.30 AP M2
Obliquity:	30
Date:	7-Jul-08

Shot #	Velocity (ft/s)	Velocity (m/s)	Result
7255	2439	744	PP -
7256	2481	756	PP -
7257	2573	784	CP +
7258	2523	769	CP +
7259	2501	763	CP +
7260	2449	747	PP -

Low CP	2501
High PP	2481

	(ft/s)	m/s
V50	2494	760
Std Dev	50	15
Vel Spread	134	41
ZMR	0	0

Plate Type:	Armox 600T
Nominal Thickness (mm)	7
Nominal Thickness (in)	0.276
Measured Thick. (in)	0.292
BHN	627
Penetrator:	.30 AP M2
Obliquity:	30
Date:	1-Jul-08

Shot #	Velocity (ft/s)	Velocity (m/s)	Result
7240	2770	845	PP -
7241	2911	888	CP +
7242	2864	873	CP +
7243	2801	854	PP -
7244	2808	856	PP -
7245	2840	866	CP +

Low CP	2840
High PP	2808

	(ft/s)	m/s
V50	2832	863
Std Dev	50	15
Vel Spread	141	43
ZMR	0	0

Plate Type:	Armox 600T
Nominal Thickness (mm)	8
Nominal Thickness (in)	0.315
Measured Thick. (in)	0.329
BHN	600
Penetrator:	.30 AP M2
Obliquity:	30
Date:	30-Jun-08

Shot #	Velocity (ft/s)	Velocity (m/s)	Result
7233	2790	851	PP
7234	2991	912	CP +
7235	2961	903	CP +
7236	2879	878	PP -
7237	2927	892	CP +
7238	2928	893	PP -
7239	2866	874	PP -

Low CP	2927
High PP	2928

	(ft/s)	m/s
V50	2925	892
Std Dev	47	14
Vel Spread	125	38
ZMR	1	0

Plate Type:	Armox 600T
Nominal Thickness (mm)	8
Nominal Thickness (in)	0.315
Measured Thick. (in)	0.329
BHN	600
Penetrator:	.50 AP M2
Obliquity:	30
Date:	1-Jul-08

Shot #	Velocity (ft/s)	Velocity (m/s)	Result
6765	2227	679	PP -
6766	2273	693	CP +
6767	2247	685	PP -
6768	2303	702	CP +
6769	2280	695	PP -
6770	2291	698	CP +

Low CP	2273
High PP	2280

	(ft/s)	m/s
V50	2270	692
Std Dev	28	9
Vel Spread	76	23
ZMR	7	2

Plate Type:	Armox 600T
Nominal Thickness (mm)	10
Nominal Thickness (in)	0.394
Measured Thick. (in)	0.41
BHN	600
Penetrator:	.50 AP M2
Obliquity:	30
Date:	1-Jul-08

Shot #	Velocity (ft/s)	Velocity (m/s)	Result
6759	2425	739	PP -
6760	2540	774	CP +
6761	2508	765	CP +
6762	2465	752	PP -
6763	2473	754	CP +
6764	2441	744	PP -

BHN	600
Low CP	2473
High PP	2465

	(ft/s)	m/s
V50	2475	755
Std Dev	43	13
Vel Spread	115	35
ZMR	0	0

Plate Type:	Armox 600T
Nominal Thickness (mm)	12
Nominal Thickness (in)	0.472
Measured Thick. (in)	0.482
BHN	578
Penetrator:	.50 AP M2
Obliquity:	30
Date:	19-Jun-08

Shot #	Velocity (ft/s)	Velocity (m/s)	Result
6708	2735	834	CP +
6709	2633	803	PP -
6710	2682	818	PP -
6711	2713	827	PP -
6712	2768	844	CP +
6713	2729	832	CP +

Low CP	2729
High PP	2713

	(ft/s)	m/s
V50	2710	826
Std Dev	47	14
Vel Spread	135	41
ZMR	0	0

INTENTIONALLY LEFT BLANK.

NO. OF
COPIES ORGANIZATION

1 DEFENSE TECHNICAL
(PDF INFORMATION CTR
only) DTIC OCA
8725 JOHN J KINGMAN RD
STE 0944
FORT BELVOIR VA 22060-6218

1 US ARMY RSRCH DEV &
ENGRG CMD
SYSTEMS OF SYSTEMS
INTEGRATION
AMSRD SS T
6000 6TH ST STE 100
FORT BELVOIR VA 22060-5608

1 DIRECTOR
US ARMY RESEARCH LAB
IMNE ALC IMS
2800 POWDER MILL RD
ADELPHI MD 20783-1197

1 DIRECTOR
US ARMY RESEARCH LAB
AMSRD ARL CI OK TL
2800 POWDER MILL RD
ADELPHI MD 20783-1197

1 DIRECTOR
US ARMY RESEARCH LAB
AMSRD ARL CI OK PE
2800 POWDER MILL RD
ADELPHI MD 20783-1197

ABERDEEN PROVING GROUND

1 DIR USARL
AMSRD ARL CI OK TP (BLDG 4600)

NO. OF
COPIES ORGANIZATION

3 CMDR US ARMY TACOM
AMSTA TR S
T FURMANIAK
L PROKURAT FRANKS
D TEMPLETON
MS 263
WARREN MI 48397-5000

1 US ARMY TACOM
AMSTA TR R
D HANSEN
MS 271
WARREN MI 48397-5000

1 PM
SFAE GCSS HBCTS
J ROWE
MS 325
WARREN MI 48397-5000

2 NATL GROUND INTLLGNC CTR
J CRIDER
W GSTATTENBAUER
2055 BOULDERS RD
CHARLOTTESVILLE VA 22091-5391

1 CRUSADER OPM
SFAE GCSS CR E
B ROOPCHAND
BLDG 171A
PICATINNY ARSENAL NJ 07806-5000

1 DARPA
3701 N FAIRFAX DR
ARLINGTON VA 22203-1714

1 PM BFVS
SFAE GCSS W BV S
M KING
WARREN MI 48397-5000

1 NAV SURF WARFARE CTR
CARDEROCK DIV
CODE 28
R PETERSON
9500 MACARTHUR BLVD
WEST BETHESDA MD 20817-5700

2 LAWRENCE LIVERMORE NATL LAB
R LANDINGHAM L372
JOHN REAUGH L282
PO BOX 808
LIVERMORE CA 94550

NO. OF
COPIES ORGANIZATION

2 LOS ALAMOS NATL LAB
F ADDESSIO
M BURKETT
PO BOX 1663
LOS ALAMOS NM 87545

1 NAVAL RSCH LABORATORY
ATTN CODE 6684
4555 OVERLOOK AVE SW
WASHINGTON DC 20375

3 SANDIA NATL LAB
J ASAY MS 1811
L CHHABILDAS MS 1811
D CRAWFORD MS 0836, 9116
PO BOX 5800
ALBUQUERQUE NM 87185-5800

1 AIR FORCE ARMAMENT LAB
AFATL DLJW
W COOK
EGLIN AFB FL 32542

4 INST FOR ADVNCD TECH
S BLESS
H FAIR
J HODGE
R SUBRAMANIAN
3925 W BRAKER LANE
AUSTIN TX 78759-5316

1 UNIV OF DAYTON RSCH INST
KLA 14 N BRAR
300 COLLEGE PARK
DAYTON OH 45469-0182

3 SOUTHWEST RSCH INST
C ANDERSON
J RIEGEL
J WALKER
6220 CULEBRA RD
SAN ANTONIO TX 78238

4 US DEPT OF ENERGY
ALBANY RSCH CENTER
J HANSEN (2 CPS)
P TURNER (2 CPS)
1450 QUEEN AVE SW
ALBANY OR 97321-2198

1 BROWN UNIV
DIV OF ENGINEERING
R CLIFTON
PROVIDENCE RI 02912

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	UNIV OF CA SAN DIEGO DEPT OF APPL MECH & ENGR SVC RO11 S NEMAT NASSER M MEYERS LA JOLLA CA 92093-0411
2	AERONAUTICAL RSCH ASSN R CONTILIANO J WALKER PO BOX 2229 50 WASHINGTON RD PRINCETON NJ 08540
1	APPLIED RSCH ASSN INC D GRADY 4300 SAN MATEO BLVD NE STE A ALBUQUERQUE NM 87110
1	BRIGGS COMPANY J BACKOFEN 2668 PETERSBOROUGH ST HERNDON VA 222071-2443
3	CERCOM R PALICKA G NELSON B CHEN 1960 WATSON WAY VISTA CA 92083
1	CYPRESS INTERNTL A CAPONECCHI 1201 E ABINGDON DR ALEXANDRIA VA 22314
1	EICHELBERGER CONSULTANT R EICHELBERGER 409 W CATHERINE ST BEL AIR MD 21014-3613
1	EPSTEIN AND ASSN K EPSTEIN 2716 WEMBERLY DR BELMONT CA 94002
1	GENERAL RSCH CORP PO BOX 6770 SANTA BARBARA CA 93160-6770

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
6	GDLS W BURKE MZ436 21 24 G CAMPBELL MZ436 30 44 D DEBUSSCHER MZ436 20 29 J ERIDON MZ436 21 24 W HERMAN MZ435 01 24 S PENTESCU MZ436 21 24 38500 MOUND RD STERLING HTS MI 48310-3200
1	INTERNATL RSCH ASSN D ORPHAL 4450 BLACK AVE PLEASANTON CA 94566
1	DIRECTOR NASA JET PROPULSION LAB IMPACT PHYSICS GROUP M ADAMS 4800 OAK GROVE DR PASADENA CA 91109-8099
3	OGARA HESS & EISENHARDT G ALLEN D MALONE T RUSSELL 9113 LE SAINT DR FAIRFIELD OH 45014
2	ALLVAC OREMET FACLT J KOSIN B MAHONEY 530 34TH AVE SW PO BOX 460 ALBANY OR 97321
4	POULTER LAB SRI INTRNTL D CURRAN R KLOOP L SEAMAN D SHOCKEY 333 RAVENSWOOD AVE MENLO PARK CA 94025
1	TIMET J FANNING PO BOX 2128 HENDERSON NV 89009

NO. OF
COPIES ORGANIZATION

6 RMI TITANIUM CO
J BENNETT
E CHRIST
F JANOWSKI
W PALLANTE
S ROBERTSON
O YU
1000 WARREN AVE
NILES OH 44446

1 SIMULA INC
R WOLFFE
10016 SOUTH 51 ST
PHOENIX AZ 85044

3 UNITED DEFNS LIMITED PARTNERS
GROUND SYS DIV
E BRADY
R JENKINS
K STRITTMATTER
PO BOX 15512
YORK PA 17405-1512

5 MENA
R DELORME
1001 COLLEGE ST
PO BOX 258
MADISON IL 62060

1 APPLIED RSCH LAB
ACOUSTICS PROGRAM
D SWANSON
504L APPLIED SCI BLDG
UNIVERSITY PK PA 16803

1 UNIV OF VIRGINIA
DEPT OF MATERIALS SCI & ENG
SCHOOL OF ENG & APPL SCIENCE
H WADLEY
B214 THORNTON HALL
116 ENGINEERS WAY
CHARLOTTESVILLE VA 22903

1 PACIFIC NORTHWEST NATL LAB
E NYBERG
MSIN P7-82
902 BATTELLE BLVD
RICHLAND WA 99352

NO. OF
COPIES ORGANIZATION

1 CELLULAR MATERIALS INTRNTL
INC
Y MURTY
2 BOARS HEAD LANE
CHARLOTTESVILLE VA 22903

1 EMBASSY OF AUSTRALIA
COUNSELLOR DEFENCE SCIENCE
1601 MASSACHUSETTS AVE NW
WASHINGTON DC 20036-2273

ABERDEEN PROVING GROUND

1 DIR USA EBCC
SCBRD RT
5183 BLACKHAWK RD
APG EA MD 21010-5424

1 CDR USA SBCCOM
AMSCB CII
5183 BLACKHAWK RD
APG EA MD 21010-5424

1 DIR USAMSAA
AMSRD AMS D
BLDG 392

1 CDR USAATC
STEAC LI LV
E SANDERSON
BLDG 359

1 CDR US ARMY DTC
ATTN CSTE DTC TT T
M SIMON
RYAN BLDG

80 DIR USARL
AMSRD ARL D
V WEISS
AMSRD ARL SL
R COATES
T FARRAND
K KIMSEY
L MAGNESS
R MUDD
D SCHEFFLER
S SCHRAML
S SEGLETES
R SUMMERS
W WALTERS

NO. OF
COPIES ORGANIZATION

AMSRD ARL SL BE
A DIETRICH
AMSRD ARL SL BW
W BRUCHEY
AMSRD ARL WM
J SMITH
J MCCAULEY
P PLOSTINS
T WRIGHT
AMSRD ARL WM B
M ZOLTOSKI
AMSRD ARL WM BC
R ANDERSON
AMSRD ARL WM BD
D LOWRY
AMSRD ARL VT UV
S WILKERSON
AMSRD ARL WM M
J BEATTY
B DOWDING
S MCKNIGHT
AMSRD ARL WM MB
R CARTER
L KECSKES
S MATHAUDHU
D SNOHA
AMSRD ARL WM MC
W ROY
R SQUILLACIOTI
AMSRD ARL WM MD
B CHEESEMAN
E CHIN
K CHO
J MONTGOMERY
AMSRD ARL WM T
P BAKER
B BURNS
AMSRD ARL WM TA
M BURKINS (5 CPS)
W GOOCH (5 CPS)
D HACKBARTH
T HAVEL
C HOPPEL
E HORWATH
T JONES (10 CPS)
D KLEPONIS
B LEAVY
H MEYER
J RUNYEON
S SCHOENFELD
AMSRD ARL WM TB
R BANTON
R GUPTA

NO. OF
COPIES ORGANIZATION

AMSRD ARL WM TD
S BILYK
T BJERKE
D CASEM
J CLAYTON
D DANDEKAR
M GREENFIELD
Y HUANG
B LOVE
M RAFTENBERG
E RAPACKI
M SCHEIDLER
T WEERASOORIYA
AMSRD ARL WM TE
C HUMMER

NO. OF
COPIES ORGANIZATION

3 R KOCH
SSAB OXELOSUND AB
SE 613 80
OXELOSUND SWEDEN

3 AERONAUTICAL & MARITIME
RSCH LAB
N MURMAN
S C1MPOERU
D PAUL
PO BOX 4331
MELBOURNE VIC 3001
AUSTRALIA

1 ARMSCOR
L DU PLESSIS
PRIVATE BAG X337
PRETORIA 0001
SOUTH AFRICA

1 DEFENCE RSCH AGENCY
FORT HALSTEAD SEVEN OAKS
KENT TN 14 7BP
UNITED KINGDOM

1 CARLOS III UNIV OF MADRID
C NAVARRO
ESCUELA POLTEENICA SUPERIOR
C/BUTARQUE 15
28911 LEGANES MADRID
SPAIN

1 CELIUS MATERIAL TEKNIK
KARLSKOGA AB
L HELLNER
S 69180 KARLSKOGA
SWEDEN

3 CENTRE D'ETUDES GRAMAT
J CAGNOUX C GALLIC
J TRANCHET
GRAMAT 46500
FRANCE

1 MINISTRY OF DEFENCE
DGA DSP STTC G BRAULT
4 RUE DE LA PORTE D'ISSY
00460 ARMEES
F 75015 PARIS
FRANCE

NO. OF
COPIES ORGANIZATION

1 CONDAT PROJEKT GMBH
ATTN J KIERMEIR
MAXIMILIANSTR 28
SCHEYERN 85298
GERMANY

1 OSAKA UNIVERSITY
JOINING & WELDING RSCH INST
ATTN DR KATSUYOSHI KONDOH
11-1 MIHOGAOAKA IBARAKI
OSAKA 567-0047 JAPAN

2 DEFENCE PROCUREMENT AGCY
G LAUBE
W ODERMATT
BALLISTICS WPNS & COMBAT
VEHICLE TEST CTR
CH 3602 THUN
SWITZERLAND

1 TDW-EADS
ATTN M HELD
PO BOX 1340
SCHROBENHAUSEN D 86523
GERMANY

4 DEFENSE RESEARCH AGENCY
ATTN W CARSON
ATTN T HAWKINS
ATTN B JAMES
ATTN B SHRUBSALL
PORTON DOWN
SALISBURY WILTS SP04 OJQ
UNITED KINGDOM

1 DEFENCE RESEARCH &
DEVELOPMENT-VALCARTIER
ATTN R DELAGRAVE
2459 BLVD PIE XI NORTH
VAL-BELAIR QC G3J 1X5
CANADA

2 DEUTSCH FRANZOSISCHES
FORSCHUNGSINSTITUT ST LOUIS
H ERNST
H LERR
CEDEX 5 RUE DU
GENERAL CASSAGNOU
F 68301 SAINT LOUIS
FRANCE

NO. OF
COPIES ORGANIZATION

1 DIEHL GMBH AND CO
M SCHILDKNECHT
FISCHBACHSTRASSE 16
D 90552 ROTBENBACH AD
PEGNITZ
GERMANY

2 ETBS DSTI
P BARNIER
M SALLES
ROUTE DE GUERAY
BOITE POSTALE 712
18015 BOURGES CEDEX
FRANCE

1 FEDERAL MINISTRY OF DEFENCE
DIR OF EQPT & TECH LAND
RUV 2
D HAUG
POSTFACH 1328
53003 BONN
GERMANY

4 FRANHOFER INSTITUT FUR
KURZZEITDYNAMIK
ERNST MACH INSTITUT
V HOHLER
E STRASSBURGER
R TRAM
K THOMA
ECKERSTRASSE4
D 79 104 FREIBURG
GERMANY

1 MINISTRY OF DEFENCE
DGA/SPART
C CANNAVO
10 PLACE GEORGES CLEMENCEAU
BP 19
F 92211 SAINT CLOUD CEDEX
FRANCE

2 HIGH ENERGY DENSITY RSCH CTR
V FORTOV
G KANEL
IZHORSKAY STR 13/19
MOSCOW 127412
RUSSIAN REPUBLIC

1 INGENIEURBURO DEISENROTH
F DEISENROTH
AUF DE HARDT 33 35
D 5204 LOHMAR 1
GERMANY

NO. OF
COPIES ORGANIZATION

1 INST OF CHEMICAL PHYSICS
S RAZORENOV
142432 CHERNOGOLOVKA
MOSCOW REGION
RUSSIAN REPUBLIC

7 INST FOR PROBLEMS IN MATLS SCI
S FIRSTOV
B GALANOV
O GRIGORIEV
V KARTUZOV
V KOVTUN
Y MILMAN
V TREFILOV
3 KRHYZHANOVSKY STR
252142 KIEV 142
UKRAINE

1 INST FOR PROBLEMS OF STRENGTH
G STEPANOV
TIMIRY AZEVSKAYA STR 2
252014 KIEV
UKRAINE

3 INST OF MECH ENGR PROBLEMS
V BULATOV
D INDEITSEV
Y MESCHERYAKOV
BOLSHOY 61 VO
ST PETERSBURG 199178
RUSSIAN REPUBLIC

2 IOFFE PHYSICO TECH INST
E DROBYSHEVSKI
A KOZHUSHKO
ST PETERSBURG 194021
RUSSIAN REPUBLIC

1 R OGORKIEWICZ
18 TEMPLE SHEEN
LONDON SW 14 7RP
UNITED KINGDOM

2 NATL DEFENCE HDQRTRS
PMO MRCV MAJ PACEY
PMO LAV A HODAK
OTTOWA ONTARIO KIA OK2
CANADA

1 OTO BRED A
M GUALCO
VIA VALDIOCCHI 15
119136 LA SPEZIA
ITALY

NO. OF
COPIES ORGANIZATION

- | | |
|---|--|
| 2 | ROYAL NETHERLANDS ARMY
JHOENEVELD
V D BURCHLAAN 31
PO BOX 90822
2509 LS THE HAGUE
NETHERLANDS |
| 1 | DEFENCE MATERIEL ADMIN
WEAPONS DIRECTORATE
A BERG
S 11588 STOCKHOLM
SWEDEN |